

FX-806 丙烯酸改性过氯乙烯防腐面漆

FX-806 Acrylic Modified Vinyl Perchloride Anticorrosive Finish

产品特性

漆膜干燥块

Characteristics

Fast drying.

具有优良的耐腐蚀和耐潮湿性能 Excellent resistance to corrosion and humidity.

有一定的耐化学品性能, 亦有防延烧性

Offer chemical resistance, and prevent flame from spreading.

在-20℃仍可施工

Application can still be performed at -20 $^{\circ}$ C.

产品用途

主要用于化工机械、设备、管道等金属、水泥构件的防腐涂装,可防止酸、碱及化学药品的腐

蚀。

As anticorrosive coatings for metal or cement components surfaces of chemical machineries,

equipment, pipelines to protect against corrosion of acid, alkali and chemical medicines.

颜色

Uses

各色

Color

All colors

施工条件

Equipment

无气喷涂 airless spray 拍

喷嘴尺寸 nozzle orifice

压力 nozzle pressure

稀释比率 thinner ratio

适用于常规的喷涂、刷涂和辊涂

推荐 recommended

0.4~0.5mm

100~150kg/cm² 0~5%b by weight(重量比)

May be applied by spray, brush, or roller.

稀释剂

专用稀释剂

Thinner

Special thinner

混合比率

单组分

Mixing ratio

Single component

涂装膜厚

干膜: 30µm/道

湿膜:65µm/道

Film thickness

Dry film thickness:30µm/coat

Wet film thickness:65µm/coat

固体含量

40%

Solid content

40%



比重 1.05 Specific gravity 1.05 涂 覆 率 理论值: 0.11 千克/平方米/30μm 0.105 L/平方米/30μm Coverage rate Theoretical: 0.11kg/m²/30µm $0.105 L/m^2/30 \mu m$ 实际值:与表面处理,外界环境,施工方法等多种因素有关。 Actual: depending on the surface treatment, environment and application methods. 干燥时间 温度(temperature): 10℃ 20°C 30℃ Drying time 指触干燥(dry to touch): 20mins 15mins 10mins 实干(dry to handle): 3hrs 1.5hrs 1hrs 涂装间隔 Min. 最小 9hrs 7hrs 5hrs Max. 最大 Coating interval 一年 储存期限 Shelf life 12 months 包装规格 单组份包装: 20kg/桶 **Packing** One component: 20kg/bucket 表面处理 底漆(中间漆)表面应清洁干燥,无污物 The surface of primer or intermediate coat should be clean, dry and free from contamination. Surface preparation 用高压空气吹扫除去灰尘等污物 Remove any contaminants like dust by high pressure blower. 如果施工环境湿度大于70%可加入适量的过氯乙烯防潮剂 Charge moderate amounts of Vinyl Perchloride Anti Blooming Agent if relative humidity of the application environment is greater than 70%. 涂装配套 适用底材:涂刷过过氯乙烯底漆的底材或参考我公司的配套。 Substrate: the surfaces coated with Vinyl Perchloride Primer, or refer to our system. Coating system 安全注意事项 任何油漆施工中均应保证提供以下措施: Safety Precautions The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛,应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical



attention.

保证良好的通风。

Assure well-ventilated working place.

小心火灾或爆炸。

Take precautions of the risks of fire or explosion.

现场遵守一切健康安全规定。

Observe all health and safety regulations on site

提醒注意 Declaration 本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展,此中所有信息均以我方确认为准。

The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.