

## FXF50-31 酚醛耐酸漆 (各色)

## **FXF50-31 Phenolic Acid Resistant Paints**

产品特性	具有一定的耐酸作用,漆膜坚硬、光亮;					
Characteristics	A certain acid resistance with a firm and glossy paint film; 附着力极佳、耐水耐油性极好。					
	Excellent adhesion and good resistance to water and oil.					
M						
产品用途	适用于有酸性气体侵蚀的木材和金属表面防腐; An anticorrosive coating for wood and metals where the coating is to be exposed to acid gases; 但是不宜侵入稀酸内。					
Uses						
	But it shall not be immersed in dilute acid.					
颜 色	各色					
Color	All colors					
施工条件	无气喷涂 Airless spray 推荐 Recommended					
Application method	元 (現據 Alliess spray )库特 Recommended					
11	喷嘴尺寸 Nozzle tip 0.4~0.5mm					
	压力 Fluid pressure 150kg/cm²					
	稀释比率 Thinning ratio 0~10% (重量比) (by wt)					
	适用于无气喷涂、空气喷涂、刷涂及辊涂。					
	May be applied by airless spray, air spray, brush, or roller.					
稀释剂	专用稀释剂					
Thinner	Special thinner					
混合比率	主剂/固化剂=17/3(重量比)					
Mixing ratio	主剂/四化剂=1//3(单重比) Base/hardener=17/3 (by wt)					
混合使用期	温 度 (℃): 10℃ 20℃ 30℃					
Pot life	Temperature (°C):					
	混合使用期 (hrs): 12 8 6					
	Pot life (hrs):					
涂装膜厚	干膜: 50μm/道 湿膜: 85μm/道					
Film thickness	Dry film thickness:50µm /coat Wet film thickness:85µm /coat					
固体含量	68%					
Solid content						
比重						
Specific gravity						



涂 覆 率	理论值:0.12kg/m²/50μm	L/n	1²/50µm				
Coverage rate	Theoretical: $0.12 \text{kg/m}^2/50 \mu\text{m}$ L/m <sup>2</sup> /50 $\mu\text{m}$						
Č	实际值:与表面处理,外界环境,施工方法等多种因素有关。						
	Actual: depending on the surface	treatment, er	vironment a	and application	on methods.		
干燥时间	温度(℃)	10	20	30			
Drying time	Temperature ( $^{\circ}\mathbb{C}$ )						
	指触干燥(hrs)	2	1.5	1			
	Dry to touch (hrs)						
	半硬干燥(hrs)	14	10	8			
	Dry hard (hrs)						
	Min. 最小 (hrs)	14	10	8			
涂装间隔	Max. 最大 (days)						
Coating interval	war. 5400 (augu)						
<u> </u>							
储存期限	一年						
Shelf time	12 months						
包装规格	20kg/组 组份一为 17kg, 组份二为 3kg。						
Packing specification	A kit 20kg contains Part A 17kg and Part B 3kg.						
<b>丰</b>	田南小队场子子队士协场和复	Uc 라 노제 tac	O. G. <b>O.</b> F. /Ⅲ →	H	出 理 末天 上 列 g a / / / / / / / / / / / / / / / / / /		
表面处理 Surface preparation	用喷砂除锈方式除去铁锈和氧化皮达到 ISO Sa2.5 级或用电动工具处理表面达到 St3 级。 The rust and scale on the surface should be thoroughly cleaned by abrasive blasting to ISO Sa2.5 or						
Surface preparation	power tool cleaning to St3.	silould be ti	lorougilly c	icanica by abi	tasive blasting to 150 5a2.5 of		
适用下涂	耐酸底漆						
Primer coat	Acid Resistant Primer.						
安全注意事项	任何油漆施工中均应保证提供以下措施:						
Safety Precautions	The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。						
	Avoid skin and eye contact.						
	如果油漆接触到皮肤或眼睛,应用大量水冲洗并立即就医。						
	In case of skin or eye contact, flush with large amount of water and immediately get medical attention.						
	保证良好的通风。						
	Assure well-ventilated working place.						
	小心火灾或爆炸。						
	Take precautions of the risks of fire or explosion.						
	现场遵守一切健康安全规定。						
相軸公子	Observe all health and safety regulations on site.  本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能						
提醒注意 Declaration							
Declaration	制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展,此中所有信息均以我方确认为准。						
	The information given on this technical data sheet is correct to the best of our knowledge. In						
	consideration of the application conditions of the product are beyond our control, so no guarantee is						
	involved herein, namely, we are responsible for the buyers only in terms of their selecting a product.						
	All data must be clarified from our company because of the constantly improvement of our product						
	and its manufacturing process.						

