

FX 水性丙烯酸涂料

FX Waterborne Acrylic Coatings

产 品 特 性 Characteristics	可以与水稀释,不可燃; Diluted with water and nonflammable; 良好的防锈性能和优良的防水性能; Good rust resistance and excellent waterproof performance; 对裸钢底材和车间底漆有良好的附着力,干燥快; Good adhesion to bare steel and shop primer, and quick drying; 可以与存在的水性涂料或溶剂型涂料配套。 Compatible with the existing waterborne coatings or solvent-based coatings.				
产品用途 Uses	主要用于钢结构防腐、船用住舱、机舱、操控室等防腐。 Mainly used as anticorrosive coating for steel structures, ship cabins, engine rooms and control rooms.				
颜 色	各色				
Color	All colors				
) to		*			
施工条件	无气喷涂 推荐				
Application method	I)	mmended			
		~0.5mm			
	Nozzle size				
	压力 100	$\sim 150 \text{kg/cm}^2$			
	Nozzle pressure				
	稀释比率 0~3	%(重量比)by weight			
	Thinner ratio				
	适用于无气喷涂、空气喷涂、刷涂及辊涂。				
	May be applied by airless spray, air spray, brush, or roller.				
稀释剂	清水				
Thinner	Fresh water				
油 人 11、赤	A 40 1				
混合比率	单组分				
Mixing ratio	One-pack				
沙 壮 咁 亘	工時, 20 (達) 温腊 (2 /達				
涂装膜厚	干膜: 30µm/道 湿膜: 63µm/道				
Film thickness	Dry film thickness:30μm/coat Wet: film thickness:63μm/coat				
固体含量	55%				
	33/0				
Solid content					
比重	1.23				
	1.23				
Specific gravity					
必 	理込存,0.001/m²/20	0.0(51/m²/20			
涂覆率	理论值:0.08kg/m²/30μm	0.065L/m²/30μm			
Spreading rate	Theoretical: 0.08kg/m2/30µm	0.065L/m2/30μm			
	实际值:与表面处理,外界环境,施工				
	Practical: varies depending on the surface	e treatment, environment and application methods.			



干燥时间	温度℃	10	20	30				
Dying time	temperature							
	指触干燥 mins	60	30	20				
	dry to touch							
	半硬干燥 hrs	6	4	3				
	dry hard							
涂装间隔	Min. 最小 (hrs)	24	16	12				
Coating intervals	min							
	Max. 最大 (days)							
	Max							
储存期限	一年							
Shelf life	12 months							
包装规格	20 公斤/桶							
Package	20 kg/barrel							
表面处理	用清水冲去盐分以及其它水溶性污物。							
Surface preparation	Remove salt and other water-soluble contaminants by fresh water hosing							
	依照 SSPC-SP1 溶剂清洗标准除去油脂。							
	Remove oil thoroughly with suitable detergent in accordance with SSPC-SP1							
	田主正旁倉庫切除土东小笠淀棚							
	用高压空气吹扫除去灰尘等污物。 Remove dust and dirt by high-pressure air before paint application							
	Remove dust and dift by high-pressure an before paint application							
	施工前确认表面清洁干燥。							
	Confirm the surface clean and	dry						
适用底材								
Suitable substrate	适用与经预处理的裸钢、镀锌材和轻金属;							
适用上涂	The pretreated bare steel, galvanized steel or light metals							
Top coat	FX 水性丙烯酸底漆或参考我公司配套 EX Waterborne Actualic Primer, or refer to our company							
安全注意事项	FX Waterborne Acrylic Primer, or refer to our company 任何油漆施工中均应保证提供以下措施:							
Safety Precautions	任刊沺漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications:							
Safety Precautions	ine following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。							
	Avoid skin and eye contact.							
	如果油漆接触到皮肤或眼睛,应用大量水冲洗并立即就医。							
	In case of skin or eye contact, flush with large amount of water and immediately get medical							
	attention.							
	保证良好的通风。							
	Assure well-ventilated working place.							
	小心火灾或爆炸。							
	Take precautions of the risks of fire or explosion.							
	现场遵守一切健康安全规定。							
	Observe all health and safety regulations on site.							



提醒注意 Declaration

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展,此中所有信息均以我方确认为准。

The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.